

Correlation effects on the band gap of conducting polymers

C.Q. Wu*

Max-Planck-Institut für Festkörperforschung, 7000 Stuttgart 80

Federal Republic of Germany

(Received 31 August 1992)

By applying the projection technique to the computation of excitation energies, we study the correlation effects on the band gap of conducting polymers. In the presence of an additional electron or hole, the correlation induces a polarization cloud around the additional particle, which forms a polaron. For the excitation energy of a polaron, there is a competition between a *loss* of the correlation energy in the ground state and a *gain* of polarization energy. For the Hubbard interaction, the *loss* of correlation energy is dominant and correlations increase the band gap. However, for long-range interactions, the *gain* of polarization energy is dominant and correlations decrease the band gap. Screening the long-range interaction suppresses the *gain* of the polarization energy so that correlations again increase the band gap. A small dimerization is always favorable to the correlation effects. For *trans*-polyacetylene, we obtain the on-site repulsion $U = 4.4$ eV and the nearest-neighbor interaction $V = 0.8$ eV. The screening of π electrons due to the polarizability of σ electrons is quite strong.

Ms number BV4805. PACS numbers: 71.10.+x, 71.45.Gm, 77.30.+d

I. INTRODUCTION

In conducting polymers, such as *trans*-polyacetylene, the importance of electron-electron interactions has been widely accepted. Many physical phenomena, for example, the nonvanishing negative spin density on alternate carbon atoms [1], the relative ordering between states 2^1A_g and 1^1B_u [2], the optical absorption associated with neutral soliton [3], etc., should be interpreted by coping with electron-electron interactions, or more precisely, with electron correlations. But how strong are the correlations? This question has been argued for many years. A number of theories have been developed over the years to treat electron correlation in polyacetylene, among them are the mean field and perturbation theories [4,5,6], the valence bond analysis [7], the Monte Carlo calculation [8,9], Local Ansatz method [10,11], and the correlated-basis-function theory [12,13]. Comparison of these results with experiments has led to conflicting claims about the strength of electron correlations.

The band gap is an important physical quantity which is strongly dependent on electron correlations. It can be determined by the optical absorption and for *trans*-polyacetylene, a value of 1.8 eV is found [14]. It is well known that calculated band gaps come out much too large when the independent-electron or self-consistent field (SCF) approximation is made.

Recently, König and Stollhoff [15] performed an *ab initio* calculation for the ground state of polyacetylene. By fitting the dependence of the total energy on the dimerization, they were able to determine the on-site electron-electron interaction $U = 11.5$ eV as well as the effective interaction of electrons on nearest neighbor sites, $V = 2.4$ eV. When the energy gap is computed within SCF approximation a value of 6.9 eV is found, which is much larger than the observed one of 1.8 eV. The difference between these two values is apparently due to correlations.

The projection technique [16], developed recently by Fulde and his coworkers [17,18], has been successfully applied to both weakly and strongly correlated electron systems [19,20]. In this paper, the technique is applied to the calculation of the excited states of conducting polymers. One advantage of the technique is that it works on $\mathbf{r}$ instead of $\mathbf{k}$ space. This enables one to generate with increasing accuracy the local correlation hole around an electron in the conduction band and a hole in the valence band and to interpret physically the different contributions to it. They are carefully studied both for an on-site Hubbard type interaction and for long-range interactions. The polarizability of σ electrons enters the present calculations as an additional screening mechanism of the π electrons.

This paper is organized as follows. In the next section, we describe the model Hamiltonian which we use in this work. In Sec.III, the projection technique for excited states is described and the excitation energies are given. The competition between a *loss* of the correlation energy in the ground state and a *gain* of the polarization energy is shown. In Sec.IV, we give the correlation gap of conducting polymers under the scheme of the projection technique. In Sec.V, the numerical results are given, both for the Hubbard and long-range interactions. They are compared with the exact solution at the undimerized and the independent dimer limits. In the last section, we discuss the results we obtained and the screening mechanism of π electron interactions for *trans*-polyacetylene. In the appendixes, we give some details of evaluating and the gap corrections by second-order perturbation theory.

II. MODEL HAMILTONIAN

The π -electron system of one-dimensional conducting polymers can be described by the Pariser-Parr-Pople (PPP) model [21],

$$H = H_{\text{SSH}} + H_{\text{inter}}, \quad (2.1)$$

where,

$$H_{\text{SSH}} = - \sum_{l,s} [t_0 - \alpha(u_{l+1} - u_l)] (c_{l+1s}^\dagger c_{ls} + h.c.) + \frac{1}{2} K \sum_l (u_{l+1} - u_l)^2 \quad (2.2)$$

is the Su-Schrieffer-Heeger (SSH) Hamiltonian [22], $c_{ls}^\dagger$ and c_{ls} are electron creation and annihilation operators at site l and with spin $s (= \alpha, \beta)$, u_l is the deviation of the l -th site from the equilibrium position (with equal distance between sites), the nearest-neighbor hopping integral between l - and $l + 1$ -th sites has been taken as a linear function of the bond modulation $u_{l+1} - u_l$, and the last term in Eq.(2.2) is the elastic energy of this one-dimensional lattice. Furthermore,

$$H_{\text{inter}} = \frac{1}{2} U \sum_l \rho_l \rho_l + \frac{1}{2} \sum_{l,l'}' V_{ll'} \rho_l \rho_{l'} \quad (2.3)$$

is the electron-electron interaction, which includes an on-site Hubbard term U and off-site interactions $V_{ll'}$ between electrons on site l and l' , and $\rho_l = c_{l\alpha}^\dagger c_{l\alpha} + c_{l\beta}^\dagger c_{l\beta} - 1$ the net charge density. The prime in the second summation term implies $l \neq l'$.

For the calculation of ground state, an effective short-range potential, *i.e.* Hubbard or extended Hubbard model (which includes nearest-neighbor repulsion) is commonly used to account for π -electron interaction in polymers. However, when the system is away from the fully-shell electron distribution, long-range polarizations become important. So it is better to use a long-range potential for a correct description of π -electron interactions in excited states. The interaction range depends on the screening by the polarizability of σ electrons in the system. Various empirical formulas [21] for this long-range potential of π electrons have been worked out. Here we use Ohno's formula [23,21] for the interaction $V_{ll'}$, which is given by

$$V_{ll'} = \frac{U}{\sqrt{1 + (r_{ll'}/r_0)^2}}. \quad (2.4)$$

Here, $r_0 \approx 1.29 \text{\AA}$, $r_{ll'}$ is the distance between sites l and l' in unit of $\text{\AA}$ and $U = 11.13 \text{ eV}$. Roughly speaking, for polyacetylene, the carbon bond angle is 120° and average distance between the nearest-neighbor sites is $1.4 \text{\AA}$.

For a dimerized lattice ($u_l = \pm u$), the SSH Hamiltonian can be diagonalized exactly. Within Hartree-Fock approximation, we can obtain a self-consistent solution by including the exchange parts of the interaction (2.3). However, instead of a self-consistent HF Hamiltonian, we simply start from the following effective single-particle Hamiltonian,

$$H_0 = -t \sum_{ls} [1 \pm z] (c_{l+1s}^\dagger c_{ls} + h.c.), \quad (2.5)$$

where, $4t$ is the energy band-width and z is the gap order parameter, $+$ for long bonds and $-$ for short bonds. Physically, there are two factors to influence the values of these two effective quantities t and z , besides the bare single-particle contribution, which gives t_0 and $2\alpha u/t_0$ respectively. One is the exchange-interaction contribution, which results from off-site interactions. For the extended Hubbard model, this exchange-interaction gives

$$t = t_0 + V\overline{m}, \quad (2.6a)$$

$$z = \frac{2\alpha u + V\delta m}{t_0 + V\overline{m}}, \quad (2.6b)$$

where $\overline{m}$ and δm are defined by $\langle c_{ls}^\dagger c_{l+1s} \rangle = \overline{m} \pm \delta m$ [24]. For a long-range interaction, we only consider an effective change on the nearest-neighbor hopping instead of explicitly including these hopping terms beyond the nearest-neighbors [10]. Other is the correlation contribution [11], which reduces the band-width and increases the gap order parameter. While the treatment of exchange contributions is Hartree-Fock approximation, the inclusion of correlation contributions implies that we have gone beyond the mean field theory. Mathematically, t and z are determined by minimization of the total (both mean-field and correlation) energy expectation value of the Hamiltonian (2.1) in the ground state. It has been known [11] that the correlation contribution to the parameter z becomes important and makes the total energy much lower in the interaction region ($U > 2t$), and with this contribution the calculation using local ansatz is valid until intermediate interaction ($U \sim 4t$).

In the Hamiltonian (2.5) we divide the operator c_{ls} into two parts, *i.e.*, the electron operator in conduction band a_{ls} and the hole operator in valence band b_{ls} ,

$$c_{ls} = a_{ls} + b_{l\bar{s}}^\dagger, \quad (2.7)$$

where,

$$a_{ls} = \frac{1}{\sqrt{N}} \sum_k e^{ikl} [i \sin \phi_k + (-1)^l \cos \phi_k] a_{ks}, \quad (2.8a)$$

$$b_{l\bar{s}}^\dagger = \frac{1}{\sqrt{N}} \sum_k e^{ikl} [\cos \phi_k + i(-1)^l \sin \phi_k] b_{-k\bar{s}}^\dagger, \quad (2.8b)$$

$\bar{s} = -s$, the summation is over a reduced Brillouin zone $(-\pi/2, \pi/2]$, and the lattice constant has been taken as unit. The Hamiltonian (2.5) becomes

$$H_0 = 2t \sum_{k,s} \epsilon(k) (a_{ks}^\dagger a_{ks} + b_{ks}^\dagger b_{ks} - 1), \quad (2.9)$$

and the electron energy spectrum (in unit of $2t$)

$$\epsilon(k) = \sqrt{\cos^2 k + z^2 \sin^2 k}. \quad (2.10)$$

The transformation angle ϕ_k is defined by

$$\tan \phi_k = \frac{z \sin k}{\epsilon(k) + \cos k}. \quad (2.11)$$

For a half-filling case, the ground state $|0\rangle$ is the vacuum of the electron operator a_{ks} and hole operator b_{ks} , so that it is also the vacuum of operators a_{ls} and b_{ls} .

We define the correlation functions $P_{ll'}$ and $Q_{ll'}$ [10] as follows

$$P_{ll'} = \langle c_{ls}^\dagger c_{l's} \rangle = \langle b_{l\bar{s}} b_{l'\bar{s}}^\dagger \rangle, \quad (2.12a)$$

$$Q_{ll'} = \langle c_{ls} c_{l's}^\dagger \rangle = \langle a_{ls} a_{l's}^\dagger \rangle, \quad (2.12b)$$

and the anticommutators for the operators a and b are

$$\{a_{ls}, a_{l's'}^\dagger\} = \delta_{ss'} Q_{ll'}, \quad (2.13a)$$

$$\{b_{ls}, b_{l's'}^\dagger\} = \delta_{ss'} P_{ll'}. \quad (2.13b)$$

Explicit expressions for these functions are given in Appendix A. We will need them in the calculations of the following sections.

Substituting Eq.(2.7) into the interaction (2.3), we have the two-particle part as follow [24],

$$H_1 = \sum_m V_m O_m, \quad (2.14)$$

where,

$$O_m = O_m^{(1)} + (O_m^{(2)} + h.c) + (O_m^{(3)} + h.c), \quad (2.15)$$

and

$$\begin{aligned} O_m^{(1)} = \sum_{lss'} \{ & (a_{ls}^\dagger a_{l+ms'}^\dagger a_{l+ms'} a_{ls} + b_{ls}^\dagger b_{l+ms'}^\dagger b_{l+ms'} b_{ls}) \\ & - (a_{ls}^\dagger b_{l+ms'}^\dagger b_{l+ms'} a_{ls} + a_{l+ms}^\dagger b_{ls'}^\dagger b_{ls'} a_{l+ms}) \\ & + (a_{ls}^\dagger b_{l\bar{s}}^\dagger b_{l+ms'} a_{l+ms'} + a_{l+ms}^\dagger b_{l\bar{s}}^\dagger b_{l\bar{s}} a_{ls'}) \} \end{aligned} \quad (2.16a)$$

is the interaction between electron-electron, hole-hole and electron-hole;

$$O_m^{(2)} = \sum_{lss'} a_{ls}^\dagger a_{l+ms'}^\dagger b_{l+ms'}^\dagger b_{l\bar{s}}^\dagger \quad (2.16b)$$

is the spontaneous creation of two electron-hole pairs and

$$\begin{aligned} O_m^{(3)} = \sum_{lss'} (& a_{ls}^\dagger a_{l+ms'}^\dagger b_{l+ms'}^\dagger a_{ls} + a_{l+ms}^\dagger a_{ls'}^\dagger b_{l\bar{s}}^\dagger a_{l+ms} \\ & + b_{ls}^\dagger b_{l+ms'}^\dagger a_{l+ms'}^\dagger b_{ls} + b_{l+ms}^\dagger b_{ls'}^\dagger a_{l\bar{s}}^\dagger b_{l+ms}) \end{aligned} \quad (2.16c)$$

is the creation of an electron-hole pair through the scattering of an electron or a hole. We have taken the translation invariance for the interaction coefficients, *i.e.*, $V_m = V_{l,l+m}$ for $m \neq 0$ and $V_0 = U/2$. The one-particle part of interaction (2.3) has been absorbed into the effective Hamiltonian (2.5) as the exchange contribution.

III. PROJECTION TECHNIQUE

We consider the case an electron or hole is added to the half-filled system. The excitation energy is defined by

$$\varepsilon(k) = E_1(k) - E_0 \quad (3.1)$$

and is contained in the one-particle correlation function

$$R_s(k, \tau) = \langle g | c_{ks} e^{-\tau(H-E_0)} c_{ks}^\dagger | g \rangle. \quad (3.2)$$

Here, $|g\rangle$ is the ground state of the half-filled system, E_0 is the corresponding energy, $c_{ks}^\dagger$ creates an electron ($a_{ks}^\dagger$) or a hole ($b_{ks}^\dagger$), and $E_1(k)$ is the energy for the system with the additional particle. Within the quasiparticle approximation, the correlation function reduces to

$$R_s(k, \tau) = \langle g | c_{ks} c_{ks}^\dagger | g \rangle e^{-\tau \varepsilon(k)}.$$

The quasiparticle energy $\varepsilon(k)$ shows up as a pole of its Laplace transformation $R_s(k, x)$, which has been shown [18] to be

$$R_s(k, x) = (c_{ks}^\dagger \Omega | \frac{1}{x - (L_0 + H_1)} c_{ks}^\dagger \Omega). \quad (3.3)$$

In the above, we have used a bilinear form in Liouville space

$$(A|B) = \langle 0 | A^\dagger B | 0 \rangle^c, \quad (3.4)$$

the index c expresses the cumulant production [16], which is defined in Appendix B. The Liouville operator L_0 acting on any operator A gives

$$L_0 A = [H_0, A]_-, \quad (3.5)$$

and

$$\Omega = \lim_{x \rightarrow 0} (1 + \frac{1}{x - (H_1 + L_0)} H_1), \quad (3.6)$$

which transforms the ground state of H_0 ($|0\rangle$) into the exact ground state ($|g\rangle$) [16].

Now, we divide the Liouville space R into a relevant part R_0 and an irrelevant part R_1 . Let R_0 be spanned by a set $\{A_\nu\}$ of elements $|A_\nu\rangle$. Then the projector [16]

$$P = \sum_{\mu\nu} |A_\mu\rangle \chi_{\mu\nu}^{-1} \langle A_\nu| \quad (3.7)$$

projects onto the space R_0 , and $\chi_{\mu\nu} = (A_\mu | A_\nu)$.

Within this relevant space R_0 , we have

$$R_s(k, x) = \sum_{\mu, \nu} (c_{ks}^\dagger \Omega | A_\mu) \chi_{\mu\nu}^{-1} \tilde{R}_\nu(k, x), \quad (3.8)$$

where $\tilde{R}_\nu(k, x)$ denotes the set of functions

$$\tilde{R}_\nu(k, x) = (A_\nu | \frac{1}{x - P(L_0 + H_1)} P c_{ks}^\dagger \Omega). \quad (3.9)$$

Then we have the equation

$$\sum_{\eta, \mu} (x \chi_{\nu\eta} - \omega_{\nu\eta}) \chi_{\eta\mu}^{-1} \tilde{R}_\mu(k, x) = (A_\nu | P c_{ks}^\dagger \Omega) \quad (3.10)$$

with

$$\omega_{\mu\nu} = (A_\mu | (L_0 + H_1) A_\nu). \quad (3.11)$$

The excitation energies $\varepsilon(k)$ are given by the poles of $R_s(k, x)$ or $\tilde{R}_\nu(k, x)$, so are the solutions of the following equation

$$\det\{x \chi_{\mu\nu} - \omega_{\mu\nu}\} = 0, \quad (3.12)$$

if we choose the elements A_μ , which span the relevant space R_0 , so that $(A_\mu | c_{ks}^\dagger \Omega) \neq 0$.

In the half-filled ground state, the electron distribution is fully-shell. The correlation interaction (2.14) would give rise to spontaneous excitations of electron-hole pairs. These spontaneous excitations lower the total energy. In the presence of an additional electron or hole, the correlation causes two processes: one is the blocking of the spontaneous excitations of electron-hole pairs if these excitations are associated with the extra particle; other is the excitation of electron-hole pairs through the scattering of the extra particle. The former (which we use operator S_μ^η to describe) gives rise to a *loss* of the correlation energy in ground state so that the excitation energy is increased. And the latter (which we use S_μ^π to describe) is a polarization process, which decreases the excitation energy by the *gain* of the polarization energy. These two processes induce a polarization cloud around the extra particle so that an electron polaron or a hole polaron is formed. Here we set $\{A_\mu\} = \{c_{ks}^\dagger\} \oplus \{S_\mu^\pi c_{ks}^\dagger\} \oplus \{c_{ks}^\dagger S_\mu^\eta\}$, where $\{S_\mu^\pi\}$ are the operators, which do not commute with the extra particle creation operator $c_{ks}^\dagger$ while $\{S_\mu^\eta\}$ commute with the operator $c_{ks}^\dagger$. Then we can rewrite the excitation energy as two parts

$$\varepsilon(k) = 2t \cdot \epsilon(k) + \varepsilon^{\text{corr}}(k), \quad (3.13)$$

i.e., the mean-field energy spectrum and correlation contribution. The latter is combined by two parts, too,

$$\varepsilon^{\text{corr}}(k) = \varepsilon^\pi(k) + \varepsilon^\eta(k), \quad (3.14)$$

where

$$\varepsilon^\pi(k) = - \sum_\mu \pi_\mu(k) (c_{ks}^\dagger | H_1 S_\mu^\pi c_{ks}^\dagger) \quad (3.15a)$$

is the *gain* of the energy from the polarization process with the extra particle, and

$$\varepsilon^\eta(k) = \sum_\mu \eta_\mu(k) (c_{ks}^\dagger | H_1 c_{ks}^\dagger S_\mu^\eta) \quad (3.15b)$$

is the *loss* of the correlation energy in the ground state due to the extra particle.

When the mutual influence of the two types correlation is neglected by set $(S_\mu^\pi c_{ks}^\dagger | H_1 c_{ks}^\dagger S_\nu^\eta) \simeq 0$, which we believe is small and is negligible for a non-strong interaction (see Appendix C), then we can write down

$$\pi_\mu(k) = \sum_\nu C_{\mu\nu}^{-1}(\pi) (S_\nu^\pi c_{ks}^\dagger | H_1 c_{ks}^\dagger), \quad (3.16a)$$

$$\eta_\mu(k) = \sum_\nu C_{\mu\nu}^{-1}(\eta) (c_{ks}^\dagger S_\nu^\eta | H_1 c_{ks}^\dagger). \quad (3.16b)$$

The coefficients are the inversions of matrices $C(\pi)$ and $C(\eta)$, which are given by

$$C_{\mu\nu}(\pi) = (S_\mu^\pi c_{ks}^\dagger | [L_0 + H_1 - \varepsilon(k)] S_\nu^\pi c_{ks}^\dagger), \quad (3.17a)$$

$$C_{\mu\nu}(\eta) = -(c_{ks}^\dagger S_\mu^\eta | [L_0 + H_1 - \varepsilon(k)] c_{ks}^\dagger S_\nu^\eta). \quad (3.17b)$$

When the mutual influences of the correlated excitations and the polarized scatterings are taken into account, the expressions for $\pi_\mu(k)$ and $\eta_\mu(k)$ become somewhat more complex.

From the expressions (3.17), we notice that both the *loss* of the correlation energies and the *gain* of polarization energies are dependent [16] of the exact excitation energy $\varepsilon(k)$. This dependence comes from the non-zero of susceptibilities $\chi_{\mu\nu}$. It makes the excited energies must be obtained self-consistently and results in a narrowing of energy bands [25]. The more important is that, we will see in Sec.V, the dependence ensures that its results are correct for intermediate interaction strength.

IV. CORRELATION GAP

A band gap in a semiconductor is the energy it costs to move an electron on the top of valence band to the bottom of conduction band. In an electron-hole picture it is the minimum energy to create an electron-hole pair. Here, we define the *correlation gap* E_{CG} as a contribution of the correlation effect, *i.e.*, it is the difference between the exact band gap and the mean-field band gap

$$E_{CG} = E_{\text{gap}} - E_{\text{gap}}^{\text{HF}}. \quad (4.1)$$

For our case where there exists the symmetry of electrons and holes, the excitation energies of an electron polaron and a hole polaron are same. So the *correlation gap* should be twice of the excitation energies of the polaron $\varepsilon^{\text{corr}}(k_0)$ ($k_0 = \pi/2$), if the interaction between the electron polaron and hole polaron — the excitonic effect — is neglected. We leave this excitonic effect in this system as a separate study.

For the calculation of this excitation energy, we should first choose the polarized scattering operator S_μ^π and the correlated excitation operator S_μ^η . When the interaction is not strong, we can choose

$$S_{ij}^\pi = \frac{1}{2} \sum_{\sigma, \sigma'} a_{i\sigma}^\dagger b_{i\bar{\sigma}}^\dagger a_{j\sigma'}^\dagger a_{j\sigma'} \quad (4.2a)$$

and

$$S_{ij}^\eta = \frac{1}{2} \sum_{\sigma, \sigma'} a_{i\sigma}^\dagger b_{i\bar{\sigma}}^\dagger a_{j\sigma'}^\dagger b_{j\bar{\sigma}'}^\dagger. \quad (4.2b)$$

These operators span a relevant space R_0 for the case an electron is added into the conduction band. The physical meaning of the two kinds of operators has been discussed in the previous section.

The choice of the above operators means that we do not break the spin symmetry. It is correct for a dimerized system, where mean-field ground state is of bond order waves (BOW) or charge density wave (CDW), without spin density waves (SDW). However, for a uniform lattice — the undimerized limit — the SDW would play a non-negligible role. It leads the calculation using the above operators underestimate the energy gap. Furthermore, we have only considered two electron-hole pairs excitations, which is enough only for a non-strong interaction. As shown in the calculation for ground state, it works until $U \sim 4t$ [11]. This is enough for the polymers like polyacetylene, where $U \sim 4t_0$. We will see it also holds for excited states in the following section. However, for $U > 4t$, the system will undergo a spin-Peierls transition, there the spin-spin interaction is dominant. This is not the regime we interest in this paper.

With the translation invariance, we reduce the dimension of relevance space R_0 by using the following operators,

$$S_d^\pi = \sum_i S_{i,i+d}^\pi, \quad (4.3a)$$

$$S_d^\eta = \sum_i S_{i,i+d}^\eta. \quad (4.3b)$$

Now we write down the following four kinds of matrices: 1. susceptibility-matrix $(S_d^\pi a_{ks}^\dagger | S_{d'}^\pi a_{ks}^\dagger)$, $(S_d^\eta a_{ks}^\dagger | S_{d'}^\eta a_{ks}^\dagger)$; 2. projection matrix $(a_{ks}^\dagger | H_1 S_d^\pi a_{ks}^\dagger)$, $(a_{ks}^\dagger | H_1 S_d^\eta a_{ks}^\dagger)$; 3. hopping matrix $(S_d^\pi a_{ks}^\dagger | H_0 S_{d'}^\pi a_{ks}^\dagger)$, $(S_d^\eta a_{ks}^\dagger | H_0 S_{d'}^\eta a_{ks}^\dagger)$ and 4. interaction matrix $(S_d^\pi a_{ks}^\dagger | H_1 S_{d'}^\pi a_{ks}^\dagger)$, $(S_d^\eta a_{ks}^\dagger | H_1 S_{d'}^\eta a_{ks}^\dagger)$. They should be evolved before the calculation of excitation energies. These matrices are given in Appendix B.

V. NUMERICAL RESULTS

A. Hubbard interaction

We consider Hubbard interaction in this subsection based on the general formula established in the previous two sections. For such a short-range interaction, we first choose only on-site local operators S_d^π and S_d^η with $d = 0$ as the elements of set $\{A_\mu\}$. With this choice, we have the expressions for excitation energies

$$\varepsilon^\pi(k_0) = -\frac{a_\pi}{b_\pi - \varepsilon(k_0)} \cdot U^2, \quad (5.1a)$$

$$\varepsilon^\eta(k_0) = \frac{a_\eta}{b_\eta - \varepsilon(k_0)} \cdot U^2, \quad (5.1b)$$

where, the coefficients a and b are as follows

$$a_\pi = \sum_l R_l P_l^3, \quad (5.2a)$$

$$b_\pi = 3 \sum_l E_l R_l P_l^2 / a_\pi; \quad (5.2b)$$

and

$$a_\eta = \sum_l (-1)^l R_l P_l^3, \quad (5.3a)$$

$$b_\eta = 4t\epsilon(k_0) + 3 \sum_l (-1)^l E_l R_l P_l^2 / a_\eta. \quad (5.3b)$$

The functions P_l , E_l and R_l are defined in Appendix A. The coefficients b_π and b_η are independent of Hubbard strength U because the interaction matrix vanishes here.

The equation (5.1) combined with the equations (3.14) and (3.15) determines the excitation energy $\varepsilon^{\text{corr}}(k_0)$ as well as the correlation gap E_{CG} self-consistently. For *trans*-polyacetylene, the band gap has been measured as 1.8 eV [14]. For Hubbard interaction, we will see the correlation gap E_{CG} is always positive, *i.e.*, the band gap is enhanced by the Hubbard correlation. At $z = 0.15$, which opens a band gap of 1.5 eV in the single-particle energy spectrum if $t = 2.5$ eV as taken by SSH [22], we have $a_\pi = 0.055$, $a_\eta = 0.196$, $b_\pi = 4.34t$, and $b_\eta = 4.43t$. The correlation gap E_{CG} obtained is plotted as a function of U in Fig.1 as a dashed line, while the result obtained with off-site operators d up to 10 is shown as a solid line. As to make a comparison, we have shown the second-order perturbation result as a dotted line and the Monte Carlo results [8] as points with error bars in Fig.1.

First let's see the limit of small U , where the correlation gap is of the form $\kappa U^2/t$. The result with on-site operators gives $\kappa = 0.0677$, which is about 90% of the value $\kappa = 0.0755$ calculated from the second-order perturbation theory (see Appendix C). Here we should mention that the second-order perturbation theory for the correlation gap is exact in the limit of small U for the case a finite dimerization has opened a gap. It is different with the uniform lattice ($z = 0$) case where the band gap is purely Coulomb gap [26] and the perturbation theory doesn't work. Our result can be improved greatly by include of off-site operators, for d up to 10, we obtain $\kappa = 0.0723$, which reaches 96%. From Fig.1, we can see that the off-site operators become more important when the interaction strength U goes larger, which is easy to be understood.

At $z = 0$, the undimerized limit, the exact gap is available from the paper of Lieb and Wu [26],

$$E_{\text{CG}} = U - 4t + 8 \sum_{n=1}^{\infty} (-1)^n \left[\frac{1}{2} n U - (t^2 + \frac{1}{4} n^2 U^2)^{1/2} \right], \quad (5.4)$$

which is shown in Fig.1 as a dot-dashed line. Compared with this exact solution, the correlation gap at $z = 0.15$ obtained by our projection technique is always larger even only with the on-site operators. It means the correlation gap is enhanced by a finite dimerization. However, the perturbation theory shows us that there is a critical interaction strength U_c , when U is larger than U_c , the dimerization reduces the correlation gap while it enhances the correlation gap when U is smaller than U_c . Obviously this is an artifact. The fact tells us it is important that the dependence of both the correlation energy and the polarization energy

on the exact excited energy [27] because it is the dependence which raises the correlation gap.

In Fig.2, we show the dependence of the correlation gap on the dimerization z for different interaction strengths U . At very small dimerization z , as declared previously, the result we obtained here underestimates the correlation gap because the choice of the operator set (4.3), which doesn't break the spin symmetry. Comparing with the exact solution at $z = 0$, we can see that this region is very small for small U , and it is about 0.1 for $U = 4t$. The enhancement of the correlation gap by a small dimerization is shown clearly and the correlation gap reaches its maximum around $z = 0.3$. For a larger z , the correlation gap decreases monotonously. This behavior is easy to be understood by compared with the correlation energy in the ground state [10], which is decreased by a small dimerization and after reach its minimum value it goes up monotonously with the increase of the dimerization. The reason is that for Hubbard interaction, the *loss* of correlation energy is dominant and the polarization energy is small.

At $z = 1$, the independent dimer limit, the exact correlation gap can be obtained easily,

$$E_{CG} = (U^2 + 64t^2)^{1/2} - 8t, \quad (5.5)$$

which has been indicated in Fig.2 as well as the exact solution (5.4) at $z = 0$. At the independent dimer limit, the long-range operators are not important while the high-order excitations become important for a strong interaction. Since the calculation only with low-order excitations gives a value larger than the exact result, the high-order excitations should reduce the correlation gap, which is contrary to the effect of long-range operators. So we expect that there are some cancellations between the longer-range excitations and the high-order excitations.

In the end of this subsection, we mention the work of Sun *et al.* [13], which used a screened Coulomb interaction and found the optical gap is reduced by the electron interaction if the screening is very strong. This result is not contrary to ours because as stated in their paper this reduction is due to the non-diagonal bond-charge repulsion, which we don't include in this paper.

B. Long-range interaction

For the long-range interaction, we take the Ohno formula (2.4) to parameterize the interaction coefficient $V_{ll'}$, which is dependent of the distance between the site l and l' . With a dimerization u , the change of bond lengths is $4u/\sqrt{3}$ and the bond alternation is formed. Within the mean-field approximation and only nearest-neighbor-site interaction, the relation of the dimerization u and the gap parameter z is shown in Eq.(2.6). With the longer-range interaction as well as the effect of correlation, the dependence of u and z should be determined numerically as discussed in Sec.II.

Due to the existence of the long-range interaction, the relevant space R_0 only with the on-site operators ($d = 0$) is too small to give a qualitative correct result, the inclusion of long-range operators is necessary because the polarization process is of a much longer correlation length than that of correlated excitations. With the relevant space R_0 spanned by the operators (4.3) with d up to 10, the correlation gap is shown in Fig.3(a). We can

see that it is the long-range interaction which makes the *gain* of the polarization energy becomes dominant so that the correlation gap is negative. This result means the long-range correlation reduces the mean-field energy gap, which is unphysically large from the *ab initio* self-consistent field (SCF) calculation [15]. This reduction becomes larger with the increase of a small dimerization. At about $z = 0.1$, the correlation gap has reached its minimum and then increases with the increase of the dimerization.

At $z = 0.2$, the reduction of the band gap is about 3.4 eV. For *trans*-polyacetylene, the SCF gap is 6.9 eV [15], among which the SCF dimerization contributes 1.05 eV and the exchange interaction contributes the rest. So the Coulomb gap arose from the electron-electron interaction is 2.45 eV. The deviation comes from the model interaction (2.3) which doesn't include the polarizability of σ electrons in the system. The presence of σ electrons would be favorable to the π electron excitations so that it should reduce the band gap further.

In a simple way, the polarizability of σ electrons could be considered as a screening of the π -electron interactions, *i.e.*, the Ohno interaction is screened as follows [10]

$$\tilde{V}_{ll'} = \frac{V_{ll'}}{\epsilon_0}. \quad (5.6)$$

At this moment, the on-site Hubbard interaction U is kept unchanged. With the screen for $\epsilon_0 > 2$, the correlation gap becomes positive again. It means that the screen suppresses the polarization process so that the *gain* of polarization energy is reduced and the *loss* of the correlation energy is again dominant. This is same as the correlation gap for a short-range (Hubbard) interaction qualitatively. Fig.3(b) shows the correlation gap for the screened interaction with $\epsilon_0 = 3$.

The screening reduces the π electron interaction range so that the correlation increases the gap. But at the same time, the screening reduces the exchange contribution, too, by a factor of $1/\epsilon_0$. In fact the screen decreases the energy gap, *i.e.*, the contribution of the σ electrons tends to reduce the band gap.

VI. DISCUSSIONS AND SUMMARY

First let's see the *ab initio* work of König and Stollhoff [15]. At SCF level, it gives the SCF energy gap 6.9 eV at the equilibrium dimerization $u = 3.28$ pm. The equilibrium dimerization u decreases to 2.52 pm when electron correlations are included. By fitting the ground state energy, they obtained the model parameters $\alpha = 40$ meV/pm, $K = 3.9$ meV/pm² for $t_0 = 2.5$ eV. With the above parameters, we obtain the SCF gap of 7.0 eV for the long-range interaction (2.4). Among it, the dimerization contributes $8\alpha u = 1.05$ eV while the exchange contribution $2\sum_l (-1)^{-1} V_{2l+1} P_{2l+1}$ is 5.95 eV. The agreement with *ab initio* calculation shows that the PPP model (2.1) describes the π -electrons in conducting polymers quite well.

With electron correlations, the bond alternation is reduced [28]. Then the dimerization contribution $8\alpha u$ to the band gap becomes 0.8 eV and the exchange interaction contribution to the band gap decreases 5.83 eV. With the screen (5.6), the exchange contribution to the gap is 2.49 eV for $\epsilon_0 = 2$ and is 1.52 eV for $\epsilon_0 = 3$. For the screen with a fixed on-site repulsion U ($= 11.13$ eV), the correlation gap is 4.58 eV at $\epsilon_0 = \infty$ (*i.e.*, only Hubbard

on-site interaction and no exchange contribution), and -3.39 eV at $\epsilon_0 = 1$ (*i.e.*, no screen). That gives the band gap 2.9 eV at the limit of unscreening interactions ($\epsilon_0 = 1$) and 5.4 eV at the limit of completed screening interactions ($\epsilon_0 = \infty$). Obviously in this way, the contribution of σ electrons to the band gap is contrary to the physical fact we expect, *i.e.*, the polarizability of σ electrons should reduce the band gap.

We need to consider a more realistic situation of conducting polymers: the on-site π electron interaction is not completely local, *i.e.*, it has a nonlocal part. So the on-site repulsion U would be screened by the polarizability of σ electrons from its “bare” value (11.13 eV). We take the form $U = U_0 + V$, where U_0 ($= 3.6$ eV) is the “net” on-site repulsion and V is the nearest-neighbor interaction, which is screened by σ electrons as in Eq.(5.6). In this way, at the limit of $\epsilon_0 = \infty$, the interaction is the Hubbard model with U_0 , the corresponding correlation gap is 0.42 eV, and then the band gap is 1.22 eV. That shows a reasonable reduction from the polarizability of σ electrons. To get the band gap 1.8 eV, we have to set $\epsilon_0 = 9$, a quite strong screening to π -electrons, then the exchange contribution is 0.43 eV and the correlation gap is 0.57 eV. With the screen, the on-site repulsion $U = 4.4$ eV and the nearest-neighbor interaction $V = 0.8$ eV, the interaction range is very short.

The electron-electron interaction parameters U and V we determined from the energy gap are quite different with the values obtained by fitting the groundstate energy curve of the *ab initio* calculation on dimerization. In fact it has appeared for many years that the discrepancy of the strength of electron interactions among the theoretical results based on different physical quantities. Some of the results are tabulated in Table I. It seems that it is not appropriate to talk about the strength of electron interactions in polymers based on such a simple model. The physical reason behind it is that the effective π electron interaction is strongly affected by the polarizability of σ electrons, which play a different role for different physical processes. The interaction depends on physical processes. From Table I, we can see that there are mainly two kinds of physical processes for the interaction, one is in the ground state, other is in excited states. On the ground state, the interaction is about 10 eV [11,15] while it is about 4 eV [5,6,29,30,31] on the excited states.

Finally, we summarize this work as follows. By using the projection technique for excited states, we have studied the correlation effects on the band gap of conducting polymers. In the presence of an extra particle (electron or hole), the correlation induces a polarization cloud around the extra particle, which forms a polaron. For the excitation energy of a polaron, there is a competition between a *loss* of the correlation energy in the ground state and a *gain* of the polarization energy. For a long-range interaction, the *gain* of polarization energy is dominant and the correlation decreases the band gap. A screening by the polarizability of σ electrons reduces the interaction range and suppresses the *gain* of the polarization energy due to the *correlation*. The *loss* of correlation energy becomes dominant and the correlation increases the band gap for the short-range or Hubbard interaction. A small dimerization leads to a further enhancement (reduction) of the correlation gap for the Hubbard (long-range) interaction. For *trans*-polyacetylene, we obtain the on-site repulsion $U = 4.4$ eV and the nearest-neighbor interaction $V = 0.8$ eV by fitting the band gap to 1.8 eV. The screening of π electrons due to the polarizability of σ electrons is quite strong.

ACKNOWLEDGMENTS

The author would like to thank Professor P. Fulde for his constant interest in this work and the critical reading of the manuscript. He is grateful to K. Becker, P. Fulde, P. Horsch, G. Stollhoff, X. Sun, and L. Yu for their helpful discussions. He would also like to acknowledge the financial support from the Max-Planck-Gesellschaft and the hospitality of Professor P. Fulde.

APPENDIX A: CORRELATION FUNCTIONS

The correlation functions $P_{ll'}$ and $Q_{ll'}$ defined in Eq.(2.12) have the relation

$$P_{ll'} + Q_{ll'} = \delta_{ll'}. \quad (\text{A1})$$

For even value of m and n ,

$$P_{m,n} = P_{m+1,n+1} = \frac{1}{2}\delta_{m,n}, \quad (\text{A2a})$$

$$P_{m+1,n} = P_{n,m+1} = P_{m-n+1}, \quad (\text{A2b})$$

here

$$P_{2l+1} = \frac{1}{\pi} \int_0^{\pi/2} dk \frac{\cos k \cos(2l+1)k + z \sin k \sin(2l+1)k}{\sqrt{\cos^2 k + z^2 \sin^2 k}}. \quad (\text{A3})$$

The energy correlation function is defined as

$$\begin{aligned} E_{ll'} &= (c_{ls}|H_0 c_{l's}) = (b_{l\bar{s}}^\dagger|H_0 b_{l'\bar{s}}^\dagger) \\ &= \langle b_{l\bar{s}}^\dagger H_0 b_{l'\bar{s}}^\dagger \rangle - \langle H_0 \rangle \langle b_{l\bar{s}}^\dagger b_{l'\bar{s}}^\dagger \rangle \end{aligned} \quad (\text{A4})$$

and then

$$\begin{aligned} \tilde{E}_{ll'} &= (c_{ls}^\dagger|H_0 c_{l's}^\dagger) = (a_{l\bar{s}}^\dagger|H_0 a_{l'\bar{s}}^\dagger) \\ &\equiv (-1)^{l+l'} E_{ll'}, \end{aligned} \quad (\text{A5})$$

where, we have use the cumulant production. Similarly as did for $P_{ll'}$, for even values of m and n we have

$$E_{m,n} = E_{m+1,n+1} = E_{m-n}, \quad (\text{A6a})$$

$$E_{m+1,n} = E_{n,m+1} = E_{m-n+1}, \quad (\text{A6b})$$

here,

$$E_{2l} = \frac{1}{2}t[(1+z)(P_{2l+1} + P_{-2l+1}) + (1-z)(P_{2l-1} + P_{-2l-1})], \quad (\text{A7})$$

and

$$E_{2l+1} = \frac{1}{2}t[(1+z)\delta_{l,0} + (1-z)\delta_{l,-1}]. \quad (\text{A8})$$

The polarized correlation function $R_{ll'}(k)$ is defined by

$$(a_{ks}^\dagger | a_{l's}^\dagger a_{ls} a_{ks}^\dagger) = R_{ll'}(k)/N, \quad (\text{A9})$$

N is the number of sites. Similarly, we have

$$(b_{ks}^\dagger | b_{l's}^\dagger b_{ls} b_{ks}^\dagger) = (-1)^{l+l'} R_{ll'}(k)/N, \quad (\text{A10})$$

$$R_{ll'}(k) = R_{l'l}^*(k). \quad (\text{A11})$$

For even numbers of m and n ,

$$R_{m,n}(k) = R_{m+1,n+1}(k) = R_{m-n}(k), \quad (\text{A12a})$$

$$R_{m+1,n}(k) = R_{m-n+1}(k), \quad (\text{A12b})$$

where,

$$R_{2l}(k) = e^{2ikl}, \quad (\text{A13a})$$

$$R_{2l+1}(k) = -e^{ik(2l+1)-2i\phi_k}. \quad (\text{A13b})$$

At $k_0 = \pi/2$, $R_{2l} = -R_{2l+1} = (-1)^l$, independent of the dimerization z .

APPENDIX B: COMPUTATIONS OF THE FOUR KINDS OF MATRICES

The definition [16] of cumulant productions is as follow

$$\langle 0 | A_1^\alpha \cdots A_n^\nu | 0 \rangle^c = \frac{\partial^\alpha}{\partial \lambda_1^\alpha} \cdots \frac{\partial^\nu}{\partial \lambda_n^\nu} \ln \langle 0 | \prod_{i=1}^n e^{\lambda_i A_i} | 0 \rangle_{\lambda_1=\dots=\lambda_n=0}. \quad (\text{B1})$$

Then we have the following properties:

$$\langle 0 | AB | 0 \rangle^c = \langle 0 | AB | 0 \rangle - \langle 0 | A | 0 \rangle \langle 0 | B | 0 \rangle, \quad (\text{B2a})$$

$$\begin{aligned} \langle 0 | ABC | 0 \rangle^c &= \langle 0 | ABC | 0 \rangle - \langle 0 | A | 0 \rangle \langle 0 | BC | 0 \rangle^c - \langle 0 | B | 0 \rangle \langle 0 | AC | 0 \rangle^c \\ &\quad - \langle 0 | C | 0 \rangle \langle 0 | AB | 0 \rangle^c - \langle 0 | A | 0 \rangle \langle 0 | B | 0 \rangle \langle 0 | C | 0 \rangle, \end{aligned} \quad (\text{B2b})$$

.....

In terms of the properties of cumulants and the correlation functions in Appendix A, we compute the four kinds of matrices as follows.

1. Susceptibility matrix:

$$(S_{ij}^\pi a_{ks}^\dagger | S_{i'j'}^\pi a_{ks}^\dagger) = -\frac{1}{4N} R_{ii'} P_{jj'} (2Q_{ii'} Q_{jj'} - Q_{ij'} Q_{ji'}), \quad (\text{B3a})$$

$$\begin{aligned} (S_{ij}^\eta a_{ks}^\dagger | S_{i'j'}^\eta a_{ks}^\dagger) &= \frac{1}{4N} Q_{ii'} R_{jj'} (2P_{ii'} P_{jj'} - P_{ij'} P_{ji'}) \\ &\quad + (i \rightleftharpoons j) + (i' \rightleftharpoons j') + (i, i' \rightleftharpoons j, j'). \end{aligned} \quad (\text{B3b})$$

2. Projection matrix:

$$(a_{ks}^\dagger | O_m S_{ij}^\pi a_{ks}^\dagger) = 2 \sum_l (S_{ll+m}^\pi a_{ks}^\dagger | S_{ij}^\pi a_{ks}^\dagger) + (m \rightleftharpoons -m), \quad (\text{B4a})$$

$$(a_{ks}^\dagger | O_m S_{ij}^\eta a_{ks}^\dagger) = 2 \sum_l (S_{ll+m}^\eta a_{ks}^\dagger | S_{ij}^\eta a_{ks}^\dagger). \quad (\text{B4b})$$

3. Hopping matrix:

$$(S_{ij}^\pi a_{ks}^\dagger | H_0 S_{i'j'}^\pi a_{ks}^\dagger) = -\frac{1}{4N} \{ R_{ii'} P_{jj'} (2\tilde{E}_{ii'} Q_{jj'} + 2Q_{ii'} \tilde{E}_{jj'} - Q_{ij'} \tilde{E}_{ji'} - \tilde{E}_{ij'} Q_{ji'}) \\ + R_{ii'} E_{jj'} (2Q_{ii'} Q_{jj'} - Q_{ij'} Q_{ji'}) \}, \quad (\text{B5a})$$

$$(S_{ij}^\eta a_{ks}^\dagger | H_0 S_{i'j'}^\eta a_{ks}^\dagger) = 4t\epsilon_k (S_{ij}^\eta a_{ks}^\dagger | S_{i'j'}^\eta a_{ks}^\dagger) \\ + \{ \frac{1}{4N} [(Q_{ii'} R_{jj'} + R_{ii'} Q_{jj'}) (2E_{ii'} P_{jj'} - E_{ij'} P_{ji'}) \\ + R_{ii'} \tilde{E}_{jj'} (4P_{ii'} P_{jj'} - 2P_{ij'} P_{ji'})] \\ + (i \rightleftharpoons j) + (i' \rightleftharpoons j') + (i, i' \rightleftharpoons j, j') \}. \quad (\text{B5b})$$

4. Interaction matrix:

$$(S_{ij}^\pi a_{ks}^\dagger | O_m S_{i'j'}^\pi a_{ks}^\dagger) = -\frac{1}{8N} R_{ii'} \sum_l \{ P_{jj'} Q_{li'} Q_{l+mj'} (2Q_{li} Q_{l+mj} - Q_{lj} Q_{l+mi}) \\ + P_{jj'} Q_{lj'} Q_{l+mi'} (2Q_{lj} Q_{l+mi} - Q_{li} Q_{l+mj}) \\ - 2P_{l+mj} P_{l+mj'} Q_{li'} (2Q_{li} Q_{jj'} - Q_{lj} Q_{ij'}) \\ - 2P_{l+mj} P_{l+mj'} Q_{lj'} (2Q_{lj} Q_{ii'} - Q_{li} Q_{ji'}) \\ + 4P_{lj} P_{l+mj'} Q_{l+mj'} (2Q_{lj} Q_{ii'} - Q_{li} Q_{ji'}) \\ - 2P_{lj} P_{l+mj'} Q_{l+mi'} (2Q_{lj} Q_{ij'} - Q_{li} Q_{jj'}) \\ + (m \rightleftharpoons -m) \}, \quad (\text{B6a})$$

$$(S_{ij}^\eta a_{ks}^\dagger | O_m S_{i'j'}^\eta a_{ks}^\dagger) = \frac{1}{4N} \sum_l \{ (R_{li} Q_{li'} + Q_{li} R_{li'}) Q_{l+mj} Q_{l+mj'} (2P_{ii'} P_{jj'} - P_{ij'} P_{ji'}) \\ + Q_{ii'} R_{jj'} P_{li'} P_{l+mj'} (2P_{li} P_{l+mj} - P_{lj} P_{l+mi}) \\ - [(R_{l+mi} Q_{l+mi'} + Q_{l+mi} R_{l+mi'}) Q_{jj'} + Q_{l+mi} Q_{l+mi'} R_{jj'}] \times \\ \times [P_{li'} (2P_{li} P_{jj'} - P_{lj} P_{ij'}) + P_{lj'} (2P_{lj} P_{ii'} - P_{li} P_{ji'})] \\ + [(R_{li} Q_{l+mi'} + Q_{li} R_{l+mi'}) Q_{jj'} + Q_{li} Q_{l+mi'} R_{jj'}] \times \\ \times [2P_{l+mi'} (2P_{li} P_{jj'} - P_{lj} P_{ij'}) - P_{l+mj'} (2P_{li} P_{ji'} - P_{lj} P_{ii'})] \\ + (m \rightleftharpoons -m) \} \\ + (i \rightleftharpoons j) + (i' \rightleftharpoons j') + (i, i' \rightleftharpoons j, j'). \quad (\text{B6b})$$

The matrices with the translational invariance are easily got from the above matrices.

APPENDIX C: SECOND-ORDER PERTURBATION THEORY

By use of the second-order perturbation theory, the correlation energy for the state with an extra electron in the half-filled ground state is

$$E_1^{\text{corr}}(k) = - \sum_m \frac{|\langle m | H_1 a_{ks}^\dagger | 0 \rangle|^2}{E_m - E_k}. \quad (\text{C1})$$

With the equation (2.14), we have the Hubbard interaction as

$$H_1 = \frac{1}{2} U \{ O_0^{(1)} + O_0^{(2)} + O_0^{(2)\dagger} + O_0^{(3)} + O_0^{(3)\dagger} \}, \quad (\text{C2})$$

and

$$H_1 a_{ks}^\dagger |0\rangle = \frac{1}{2} U \{O_0^{(2)} + O_0^{(3)}\} a_{ks}^\dagger |0\rangle, \quad (C3)$$

where, the first term gives the creation of two electron-hole pairs and other term gives the creation of an electron-hole pair through the scattering of the extra electron. So that there are two types of intermediate states, which have contributions to the correlation energy (C1). The contribution from the intermediate state

$$|m\rangle = a_{k_1s}^\dagger a_{k_2\bar{s}}^\dagger b_{k_3s}^\dagger b_{k_4\bar{s}}^\dagger a_{ks}^\dagger |0\rangle \quad (C4a)$$

gives the correlation energy of the half-filled ground state and the *loss* of correlation energy due to the extra electron. The contribution from the intermediate state

$$|m\rangle = a_{k_1s}^\dagger a_{k_2\bar{s}}^\dagger b_{k_3s}^\dagger |0\rangle \quad (C4b)$$

gives the *gain* of the polarization energy due to the polarized process after the additional electron was introduced. Then we rewrite the correlation energy in Eq.(C1) as

$$E_1^{\text{corr}}(k) = E_g^{\text{corr}} + E_\eta(k) + E_\pi(k), \quad (C5)$$

where, E_g^{corr} is the correlation energy of the ground state, the *loss* of correlation energy in the ground state

$$E_\eta(k_0) = \frac{U^2}{4tN^2} \sum_{k_1, k_2} \frac{1}{(\epsilon_0 + \epsilon_1 + \epsilon_2 + \epsilon_3)\epsilon_0\epsilon_1\epsilon_2\epsilon_3} (\epsilon_0\epsilon_1\epsilon_2\epsilon_3 + c_0c_1c_2c_3 + z_0z_1z_2z_3 - c_0z_1z_2c_3 - z_0c_1c_2z_3 + 2c_0c_1z_2z_3 + 2z_0z_1c_2c_3), \quad (C6a)$$

and the *gain* of the polarization energy

$$E_\pi(k_0) = -\frac{U^2}{4tN^2} \sum_{k_1, k_2} \frac{1}{(\epsilon_1 + \epsilon_2 + \epsilon_3 - \epsilon_0)\epsilon_0\epsilon_1\epsilon_2\epsilon_3} (\epsilon_0\epsilon_1\epsilon_2\epsilon_3 - c_0c_1c_2c_3 - z_0z_1z_2z_3 + c_0z_1z_2c_3 + z_0c_1c_2z_3 - 2c_0c_1z_2z_3 - 2z_0z_1c_2c_3). \quad (C6b)$$

Here, we have defined $k_3 = k_1 + k_2 - k_0$, $c_i = \cos k_i$, $z_i = z \sin k_i$ and $\epsilon_i = (c_i^2 + z_i^2)^{1/2}$. So the correlation gap is

$$\begin{aligned} E_{CG} &= 2E_\eta(\pi/2) + 2E_\pi(\pi/2) \\ &= \kappa(z)U^2/t, \end{aligned} \quad (C7)$$

where

$$\begin{aligned} \kappa(z) &= \frac{1}{2N^2} \sum_{k_1, k_2} \left\{ \frac{\epsilon_1\epsilon_2\epsilon_3 + z_1z_2z_3 - c_1c_2c_3 + 2z_1c_2c_3}{(\epsilon_1 + \epsilon_2 + \epsilon_3 + z)\epsilon_1\epsilon_2\epsilon_3} \right. \\ &\quad \left. - \frac{\epsilon_1\epsilon_2\epsilon_3 - z_1z_2z_3 + c_1c_2c_3 - 2z_1c_2c_3}{(\epsilon_1 + \epsilon_2 + \epsilon_3 - z)\epsilon_1\epsilon_2\epsilon_3} \right\} \end{aligned} \quad (C8)$$

and $k_3 = k_1 + k_2 - \pi/2$. The coefficient κ can be evaluated numerically.

In the end of this Appendix, we mention that, in the second-order perturbation theory, there is no mutual influence between the correlated excitations and the polarized scatterings, which we assume is small and is negligible until intermediate interaction strength in Sec.III.

REFERENCES

* Permanent address: Department of Physics, Fudan University, Shanghai 200433, China.

- [1] H. Thomann, L.R. Dalton, Y. Tomkiewicz, N.S. Shiren, and T.C. Clarke, Phys. Rev. Lett. **50**, 533 (1983).
- [2] B. Hudson and B. Kohler, Synth. Met. **9**, 241 (1984).
- [3] J. Orenstein, Z. Vardeny, G.L. Baker, G. Eagle, and S. Etemad, Phys. Rev. **B30**, 786 (1984).
- [4] K.R. Subbaswamy and M. Grabowski, Phys. Rev. **B24**, 2168 (1981).
- [5] S. Kivelson and D.E. Heim, Phys. Rev. **B26**, 4278 (1982).
- [6] W.K. Wu and S. Kivelson, Phys. Rev. **B33**, 8546 (1986).
- [7] Z. Soos and S. Ramasesha, Phys. Rev. **B29**, 5410 (1984); S. Mazumdar and S. Dixit, Phys. Rev. Lett. **51**, 292 (1983) and Phys. Rev. **B29**, 1824 (1984).
- [8] J.E. Hirsch, Phys. Rev. Lett. **51**, 296 (1983).
- [9] D.K. Campbell, T.A. DeGrand, and S. Mazumdar, Phys. Rev. Lett. **52**, 1717 (1984).
- [10] P. Horsch, Phys. Rev. **B24**, 7351 (1981).
- [11] D. Baeriswyl and K. Maki, Phys. Rev. **B31**, 6633 (1985).
- [12] C.Q. Wu, X. Sun, and K. Nasu, Phys. Rev. Lett. **59**, 831 (1987).
- [13] X. Sun, Z. Shuai, K. Nasu, D.L. Lin, and T.F. George, Phys. Rev. **B44**, 11042 (1991).
- [14] N. Suzuki, M. Okazaki, S. Etemad, A.J. Heeger, and A.G. MacDiarmid, Phys. Rev. Lett. **45**, 1209 (1980); **45**, 1483(1980)(E).
- [15] G. König and G. Stollhoff, Phys. Rev. Lett. **65**, 1239 (1990).
- [16] P. Fulde, *Electron Correlations in Molecules and Solids* (Springer-Verlag, Berlin, 1991).
- [17] K.W. Becker and P. Fulde, J. Chem. Phys. **91**, 4223(1989).
- [18] K.W. Becker and W. Brenig, Z. Phys. **B79**, 195 (1990).
- [19] K.W. Becker and P. Fulde, Z. Phys. **B72**, 423(1988).
- [20] K.W. Becker, H. Won and P. Fulde, Z. Phys. **B75**, 335(1989).
- [21] I. Ohmine, M. Karplus, and K. Schulten, J. Chem. Phys. **68**, 2298 (1978).
- [22] W.P. Su, J.R. Schrieffer, and A.J. Heeger, Phys. Rev. Lett. **42**, 1698 (1979); Phys. Rev. **B22**, 2099 (1980).
- [23] K. Ohno, Theor. Chim. Acta **2**, 219(1964).
- [24] H. Hayashi and K. Nasu, Phys. Rev. **B32**, 5295 (1985).
- [25] W. Borrmann and P. Fulde, Phys. Rev. **B35**, 9569(1987).
- [26] E.H. Lieb and F.Y. Wu, Phys. Rev. Lett. **20**, 1445 (1968).
- [27] S. Horsch, P. Horsch, and P. Fulde, Phys. Rev. **B28**, 5977(1983).
- [28] J.L. Brédas and A. Heeger, Phys. Rev. Lett. **63**, 2534(1989); C.Q. Wu, X. Sun, and K. Nasu, *ibid.*, **63**, 2535(1989).
- [29] E. Ehrenfreund, Z. Vardeny, O. Brafman, and B. Horovitz, Phys. Rev. **B36**, 1535(1987).
- [30] J.T. Gammel, D.K. Campbell, S. Mazumdar, S.N. Dixit, and E.Y. Loh Jr., Synth. Met. **41-43**, 3471(1991).
- [31] M. Grabowski, D. Hone, and J.R. Schrieffer, Phys. Rev. **B31**, 7850(1985).

FIGURES

FIG. 1. The correlation gap E_{CG} for the Hubbard interaction. The solid line is the result obtained with long-range operators (4.3) (d up to 10), the dashed line is the result with on-site operators (4.3) ($d = 0$), and the dotted line is the perturbation result at $z = 0.15$. And the dot-dashed line is the exact correlation gap at the undimerized limit $z = 0$ (Ref. [26]). The points with error bars are the Monte Carlo result (Ref. [8]).

FIG. 2. The correlation gap E_{CG} for the Hubbard interaction. The dots are got by the projection technique. The lines guide the eye. The circles are exact solutions.

FIG. 3. The correlation gap E_{CG} for a long-range interaction: (a) without screen $\epsilon_0 = 1$; (b) with screen $\epsilon_0 = 3$.

TABLES

TABLE I. The strength of electron interactions obtained by fitting to different physical quantities.

U (eV)	V (eV)	Physical quantities
11.5	2.4	The groundstate energy curve $E(u)$ ^a
7–9		The dimerization u and the screened force constant ^b
3–4		The spin density of a neutral soliton ^c
3.7	0.4	The resonant Raman spectra ^d
4.4	0.8	The band gap E_g ^e
3.7–6.0	0.0–2.5	The band width W , u , E_g and the LO mode ν_{LO} for $N = 8, 10$ ^f

^aRef. [15].

^bRef. [11].

^cRef. [6].

^dRef. [29].

^ePresent work.

^fRef. [30].